

## Data Sheet

## C515 Black 40° Shore Cloth Marked Abrasion Resistant Natural(NR) Rubber Sheet

Data Sheet Type	Final
Material Reference	C515
Polymer	NR
Date Issued	16/07/24



## Description

Designed for the Mining and Quarrying Industry, this Black Abrasion Resistant Natural Rubber has a diverse applications list, including Chute Lining, Shotblast Screens, Rifle Range Curtains, Road Sweeper Skirts well as applications within the Waste Water Industry.

Specifications	Values	Test Methods
Available from Stock	Yes	None
Colour	Black	None
Compression Set(22 Hours @ 70°C)	20 %	ASTM D395 Method B
Elongation at Break	600 %	ASTM D412
Highest Recommended Working Temperature	70 °C	None
Lowest Recommended Working Temperature	-40 °C	None
Shore Hardness (Shore A)	40 ° Shore	ASTM D2240
Specific Gravity	0.96 g/cm 3	ASTM D2240
Tensile Strength	22 MPA	ASTM D412

## Purposes



Abrasive Resistance



Anti-Vibration



Tear Resistant



Wear Resistant

**Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for

---

the intended use. This datasheet is subject to alteration without prior notice . All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.