

Data Sheet

Double Duty Switchboard Matting to ASTM D178 Type II Class 2

Data Sheet Type	Final
Material Reference	Double Duty Switchboard Matting
Polymer	PVC
Date Issued	16/07/24



Description

Double Duty Switchboard Matting has a PVC Surface with a Nitrile Infused Sponge base that provides protection from Electrical shocks and first class comfort and safety through the unique non-conductive sponge. This Switchboard Matting is for use in Live Working Applications and Tested to ASTM D178-01 Type II Class 2. Tested to 30,000 Volts with a Recommended Maximum Usage of up to 17000 Volts.

Specifications

Values

Test Methods

Specifications	Values	Test Methods
Abrasion Resistance	1% Lost @ 1000 Cycles	Fed Std 191A Method 5970
Coefficient of Friction	0.91 (Dry)	ASTM F1677
Dielectric Strength	30,000 Volts	ASTM D178-01
Flame Resistance	0.224 mm/sec	ASTM D178-01
Tear Strength	1212 PSI	ASTM D412

Purposes



Electrical Insulation



Flame Retardent



Tear Resistant

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.