

Data Sheet	LD15FM Plastazote® 15Kg/m3 Flame Retardant Closed Cell Vinyl Polyethylene Foam Sheets & Rolls

Data Sheet Type	Final	
Material Reference	LD15FM	
Polymer	PE	
Date Issued	20/04/24	





Specifications	Values	Test Methods
Compression Set 25% Compression (22 Hours @ 23°C) 24 Hour Recovery	8 %	BS ISO 7214 2012
Compression Set 50% Compression (22 Hours @ 23°C) 24 Hour Recovery	24 %	BS ISO 7214 2012
Compression Stress/Strain - 25%	30 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 40%	60 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 50%	90 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 60%	140 Kpa	BS ISO 7214 2012
Density	15 Kg/m3 Nominal	BS ISO 7214 2012
FMVSS302 Pass Thickenss	2 mm Minimum	FMVSS302
Highest Recommended Working Temperature	95 °C Maximum	None
Lowest Recommended Working Temperature	-70 °C Minimum	None
Shore Hardness (Shore OO)	38 ° Shore	ISO 8301 1991
Tensile Elongation	85 %	BS ISO 7214 2012
Tensile Strength	210 Kpa	BS ISO 7214 2012
Thermal Conductivity	.04 W/m.K Mean Temp of 10°C	ISO 8301 1991

Purposes



Flame Retardent

**Important Notes about this Material Data Sheet** 





This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.