

Data Sheet

P040 High Purity Graphite Packing with Inconel for High Temp Valves & Pumps

Data Sheet Type	Final
Material Reference	P040
Polymer	Graphite
Date Issued	15/12/18




Description


Manufactured from Pure Expanded Graphite containing minimum amounts of trace elements such as Sulphur & Chloride then reinforced with Inconel Wire.

Specifications	Values	Test Methods
Highest Recommended Working Temperature	500 °C	None
Inert Gas Operating Temp Range	-200 to 1000 °C	None
Maximum Linear Speed	2 m/s	None
Maximum Valve Pressure	350 bar	None
Oxidising Environment Temp Range	-200 to 450 °C	None
PH Range	0-14 PH Range	None
Steam Operating Temp Range	-200 to 650 °C	None


Purposes




Acid Resistance




Chemical Resistant




High Working Temperature




Low Working Temperature



Oil Resistance



Petrol Resistance



Steam Resistant

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to

evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice . All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.