

Data Sheet

Q062 European Manufactured 45° Shore Tan Shotblast Natural(NR) Rubber Sheet

Data Sheet Type	Final
Material Reference	Q062
Polymer	NR
Date Issued	20/05/24



Description

A European Manufactured Tan "Shotblast" Natural Rubber Material with excellent abrasion resistant properties. Designed to be used as Shotblast Curtains/Screens but since have many other abrasion resistant uses. Sometimes referred to as "Para" or "Paragum" Rubber.

Specifications	Values	Test Methods
Available from Stock	Yes in Standard Thicknesses	None
Colour	Tan	None
Elongation at Break	600 % Minimum	ASTM D412
European Union Manufactured	Yes	None
Highest Recommended Working Temperature	80 °C Maximum	None
Lowest Recommended Working Temperature	-25 °C Minimum	None
Shore Hardness (Shore A)	45 ° Shore +/- 5°	ASTM D2240
Specific Gravity	1.06 g/cm 3 +/- 0.03	ASTM D2240
Standard Roll/Sheet Size	1400mm x 10 Metres Range	None
Tensile Strength	11 MPA Minimum	ASTM D412

Purposes



Abrasive Resistance



Acid Resistance



Anti-Vibration



Ozone Resistance



Tear Resistant

**Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information,

---

figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice . All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.