

Data Sheet

Silicone Sponge 10

Data Sheet Type	Final
Material Reference	Silicone Sponge 10
Polymer	Silicone
Date Issued	29/03/24



Specifications	Values	Test Methods
Compression Set(22 Hours @ 70°C)	15 %	ISO 1856
Compression Stress/Strain - 40%	50 Kpa	ASTM D1056
Density	200 Kg/m3	ASTM D3574
Elongation at Break	140 %	ASTM D412
Flame Resistance	UL94 HB	UL94
Highest Recommended Working Temperature	230 °C	None
Lowest Recommended Working Temperature	-60 °C	None
Shore Hardness (Shore OO)	35 ° Shore	ASTM D2240
Tensile Strength	600 Kpa	ASTM D412
Water Absorption	< 5 %	ASTM D1056

Purposes



Flame Retardant



Food Contact Suitability



High Working Temperature

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice . All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.