

Data Sheet Type Final Material Reference VA35 Polymer VA (Vinyl Acetate) Date Issued 27/07/24

Description

Specifications	Values	Test Methods
Abrasion Resistance	5 mm3	5N UNE-ISO 4649
Cell Diameter	0.45 mm Typical	BS ISO 7214 2012
Compression Set 25% Compression (22 Hours @ 23°C) 1/2 Hour Recovery	11 %	BS ISO 7214 2012
Compression Set 25% Compression (22 Hours @ 23°C) 24 Hour Recovery	3.5 %	BS ISO 7214 2012
Compression Set 50% Compression (22 Hours @ 23°C) 1/2 Hour Recovery	25 %	BS ISO 7214 2012

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.