

| Data Sheet | | Viton E Heat Shrink Tubing | |
|--------------------|-------------------------------|---|-------|
| Data Sheet Type | Final | | |
| Material Reference | Viton E Heat Shrink Tubing | DE IN CITY OF THE PROPERTY OF | REACH |
| Polymer | FKM(>68% Flourine) | | |
| Date Issued | 27/07/24 | | |

Description

A heat shrinkable flexible high performance tubing manufactured from Viton E, with exceptional resistance to chemicals. The material will retain mechanical strength an flexibility following long term exposure to high temperatures.

Used for the protection of cables against contamination and high temperatures on applications in the Aerospace, marine, transport and defence industries.

Approved to VG 95-343 Part 5 Type E

Conforms to SAE-AMS-DTL 23053/12, IEC60684-3-233, PAN 6408L and MIL-R-46846

| Specifications | Values | Test Methods |
|------------------------------------|--------------------|------------------|
| Colour | Black | None |
| Dielectric Strength | 8 kv/mm | ASTM D2671 |
| Elongation at Break | 350 % | IEC 540 |
| Flame Resistance | Self Extinguishing | VG 95-343-5 5.12 |
| Low Temperature Flexibility | Pass | ASTM D2671 |
| Tensile Strength | 14 MPA | IEC 540 |
| Thermal Ageing (168 hours @ 250 c) | 300 % | VG 95-343-5 10 |
| Thermal Shock (4 hours @ 300c) | Pass | VG 95-343-5 5.9 |
| Water Absorption | < 0.1 % | ASTM D570 |

Purposes







High Working Temperature



Low Working Temperature



Oil Resistance



Petrol Resistance



Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.