

Data Sheet		1731 Commercial Food Grade Nitrile	
Data Sheet Type	Final		
Material Reference	1731		THE COURS
Polymer	NBR		REACH
Date Issued	04/11/25		


## Description

A commercial FoodSafe Grade <u>Butadiene Acrylonitrile Rubber</u> (NBR) Sheeting conforming to the requirements of <u>FDA</u> CFR 177 Sub Part C 177.2600.

Specifications	Values	Test Methods
Elongation at Break	350 %	ASTM D412
Highest Recommended Working Temperature	70 °C	None
Intermittent Working Temperature	90 °C	None
Lowest Recommended Working Temperature	-20 °C	None
Shore Hardness (Shore A)	60 ° Shore	ASTM D2240
Tensile Strength	8 MPA	ASTM D412

## Purposes







Oil Resistance



Water Resistant

## Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.