

Data Sheet

2349 EPDM/SBR Blend 60 Shore Rubber Sheeting

Data Sheet Type	Final
Material Reference	2349
Polymer	EPDM SBR
Date Issued	22/12/24



Description

A 60 Shore EPDM/SBR Blended Rubber Sheeting for General Purpose or Gasketing use. A Hybrid Rubber Sheet that will carry some performance characteristics of EPDM and some of SBR and is suitable for a variety of Lower Technology Sealing Applications.

Typically sold in Rolls that are 1.4 Metre Wide and 10 Metres Long for Thicknesses up to 8mm and 5 Metres Long for 8mm and above.

We stock this grade of Rubber Sheet in 1mm,1.5mm, 2mm,3mm,4mm, 5mm,6mm,8mm,10mm,12mm, 15mm & 25mm Thick

Rubber Rolls will normally be Palletised and sent using a National Pallet Network.

Specifications	Values	Test Methods
Available from Stock	Yes	None
Elongation at Break	250 % Minimum	ASTM D412
Highest Recommended Working Temperature	70 °C	None
Intermittent Working Temperature	90 °C Short Bursts Only	None
Lowest Recommended Working Temperature	-30 °C	None
Shore Hardness (Shore A)	60 ° Shore +/-5	ASTM D2240
Specific Gravity	1.5 g/cm 3	ASTM D2240
Standard Roll/Sheet Size	1400mm x 10 Metres Range	None
Tensile Strength	3 MPA Minimum	ASTM D412

**Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.