

Data Sheet	A075 Chemours ® White Viton ® FDA Rubber Sheet				
Data Sheet Type	Final				
Material Reference	A075 White				
Polymer	FKM(<66% Flourine) FKM(>68% Flourine)	ADDI Arima David Tyrodort free	FDA	ALLE W ZZ	REACH
Date Issued	17/09/25				

## Description

A Genuine European Manufactured Chemours ° Viton ° A

Fluoroelastomer Rubber Sheet FDA 21 CFR 177.2600 compliant. A number of Materials are referred to as

Viton however only European or USA Manufactured Material carries the

assurance of being a genuine Chemours ° Polymer. Typically used

for its resistance to High Temperatures, Oils & Chemicals.

Specifications	Values	Test Methods
Colour	Off White	None
Compression Set	23 Max %	ASTM D395 Method B
Elongation at Break	200 %	ASTM D412
Highest Recommended Working Temperature	200 °C	None
Lowest Recommended Working Temperature	-28 °C	None
Shore Hardness (Shore A)	65 ° Shore	ASTM D2240
Specific Gravity	2 Nominal g/cm 3	ASTM D792
Tensile Strength	10 MPA	ASTM D412

## Purposes



**Chemical Resistant** 



Food Contact Suitability



High Working Temperature



## Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.