

Data Sheet EV50 Evazote Closed Cell Vinyl Acetate Foam Sheets & Rolls

|                    |                    |
|--------------------|--------------------|
| Data Sheet Type    | Final              |
| Material Reference | EV50               |
| Polymer            | VA (Vinyl Acetate) |
| Date Issued        | 02/06/25           |



Description

Evazote An Inert Polyethylene Foam with EVA to make a durable and aesthetically pleasing Foam suitable for a variety of uses in a wide variety of industries including but not limited : Toys & Games, Sports & Leisure, Cosmetics & Performing Arts. This grade is a 50 Kilogram Density and is available in a wide variety of colours.

| Specifications   | Values           | Test Methods     |
|--|------------------|------------------|
| Cell Diameter  | 0.35 mm Typical  | BS ISO 7214 2012 |
| Compression Set 25% Compression (22 Hours @ 23°C)<br>1/2 Hour Recovery | 10.5 %           | BS ISO 7214 2012 |
| Compression Set 25% Compression (22 Hours @ 23°C)<br>24 Hour Recovery  | 3 %              | BS ISO 7214 2012 |
| Compression Set 50% Compression (22 Hours @ 23°C)<br>1/2 Hour Recovery | 23.5 %           | BS ISO 7214 2012 |
| Compression Set 50% Compression (22 Hours @ 23°C)<br>24 Hour Recovery  | 13 %             | BS ISO 7214 2012 |
| Compression Stress/Strain - 10%  | 30 Kpa           | BS ISO 7214 2012 |
| Compression Stress/Strain - 25%  | 51 Kpa           | BS ISO 7214 2012 |
| Compression Stress/Strain - 40%  | 82 Kpa           | BS ISO 7214 2012 |
| Compression Stress/Strain - 50%  | 115 Kpa          | BS ISO 7214 2012 |
| Density  | 50 Kg/m3 Nominal | BS ISO 7214 2012 |
| FMVSS302 Pass Thickenss  | 4 mm Minimum     | FMVSS302         |
| Highest Recommended Working Temperature                                | 65 °C Maximum    | None             |
| Horizontal Burn Rate @ 13mm Thick                                      | 0.8 mm/sec       | None             |
| Horizontal Burn Rate @ 5mm Thick                                       | 1.00 mm/sec      | None             |
| Lowest Recommended Working Temperature                                 | -70 °C Minimum   | None             |

#### **Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.