

Data Sheet LD18 Plastazote® Closed Cell Polyethylene Foam Sheets & Rolls Data Sheet Type Final Material Reference LD18

Material Reference LD18

Polymer PE

Date Issued 30/10/25





Description

LD18 Plastazote is an Inert Polyethylene Foam functional and aesthetically pleasing for a number of industries including but not limited to: Automotive, Packaging, Leisure, Cosmetics & Toys. This grade has a density of 18Kg/m3 and is available in black and white in a variety of Sheet/Roll sizes from 1mm thick and can be fabricated to virtually any thickness.

tilickiless.		
Specifications	Values	Test Methods
Cell Diameter	0.8 mm Typical	BS ISO 7214 2012
Compression Set 25% Compression (22 Hours @ 23°C) 1/2 Hour Recovery	13 %	BS ISO 7214 2012
Compression Set 25% Compression (22 Hours @ 23°C) 24 Hour Recovery	5.5 %	BS ISO 7214 2012
Compression Set 50% Compression (22 Hours @ 23°C) 1/2 Hour Recovery	27.5 %	BS ISO 7214 2012
Compression Set 50% Compression (22 Hours @ 23°C) 24 Hour Recovery	18.5 %	BS ISO 7214 2012
Compression Stress/Strain - 10%	33 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 25%	50 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 40%	81 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 50%	113 Kpa	BS ISO 7214 2012
Density	18 Kg/m3 Nominal	BS ISO 7214 2012
FMVSS302 Pass Thickenss	14 mm	FMVSS302
Highest Recommended Working Temperature	100 °C Maximum	None
Horizontal Burn Rate @ 13mm Thick	1.7 mm/sec	None
Horizontal Burn Rate @ 5mm Thick	2.2 mm/sec	None
Lowest Recommended Working Temperature	-70 °C Minimum	None
Shore Hardness (Shore OO)	50 ° Shore	ISO 8301 1991
Tear Strength	520 N/m	BS EN ISO 8067 2008
Tensile Elongation	125 %	BS ISO 7214 2012
Tensile Strength	300 Kpa	BS ISO 7214 2012
Thermal Conductivity	.0446 W/m.K Mean Temp of 10°C	ISO 8301 1991



Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.