



Data Sheet

LD33FM Plastazote® 33Kg/m3 Flame Retardant Closed Cell Polyethylene Foam Sheets & Rolls

Data Sheet Type	Final
Material Reference	LD33FM
Polymer	PE
Date Issued	02/06/26



Description

LD33FM Plastazote is an Inert Flame Retardant Polyethylene Foam functional and aesthetically pleasing for a number of industries including but not limited to: Automotive, Packaging, Leisure, Cosmetics & Toys. This grade has a density of 33Kg/m3 and is available in Black. LD33FM is available in endless Sheet/Roll sizes from 1mm thick and can be fabricated to virtually any thickness.

Specifications	Values	Test Methods
Compression Set 25% Compression (22 Hours @ 23°C) 24 Hour Recovery	4 %	BS ISO 7214 2012
Compression Set 50% Compression (22 Hours @ 23°C) 24 Hour Recovery	14 %	BS ISO 7214 2012
Compression Stress/Strain - 25%	40 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 40%	80 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 50%	120 Kpa	BS ISO 7214 2012
Compression Stress/Strain - 60%	175 Kpa	BS ISO 7214 2012
Density	33 Kg/m3 Nominal	BS ISO 7214 2012
FMVSS302 Pass Thickenss	2 mm Minimum	FMVSS302
Highest Recommended Working Temperature	100 °C Maximum	None
Lowest Recommended Working Temperature	-70 °C Minimum	None
Shore Hardness (Shore OO)	54 ° Shore	ISO 8301 1991
Tear Strength	700 N/m	BS EN ISO 8067 2008
Tensile Elongation	135 %	BS ISO 7214 2012
Tensile Strength	380 Kpa	BS ISO 7214 2012
Thermal Conductivity	.039 W/m.K Mean Temp of 10°C	ISO 8301 1991

Purposes



Flame Retardent

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.