

Data Sheet		P352		
Data Sheet Type	Final			
Material Reference	P352 Reticulated Foam			
Polymer	Polyurethane			
Date Issued	30/08/25			



Description

An Expanded Polyurethane Filter Foam for general applications

Specifications	Values	Test Methods
Air Flow	4000 l/(m ² *S)	ISO 9237
Compression Deflection	4 Kpa	ISO 3386
Density	25 Kg/m ³	ISO 845
Elongation at Break	90 %	ISO 1798
Highest Recommended Working Temperature	110 °C	None
Lowest Recommended Working Temperature	-30 °C	None
Pore Size	20 PPI	None
Tensile Strength	120 Kpa	ISO 1798

Purposes



Water Resistant



Weather Resistance

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.