

Data Sheet

Q410 60 Shore Abrasive Resistant SBR Rubber Sheet

Data Sheet Type	Final
Material Reference	Q410
Polymer	NR
Date Issued	02/01/25



Description

An European Manufactured Styrene Butadiene Rubber (SBR) Sheet

Specifications	Values	Test Methods
Elongation at Break	450 %	ASTM D412
Highest Recommended Working Temperature	70 °C	None
Lowest Recommended Working Temperature	-10 °C	None
Shore Hardness (Shore A)	60 ° Shore	ASTM D2240
Specific Gravity	1.16 g/cm 3	ASTM D2240
Tear Strength - Angle	30 kg/cm	UNE ISO 34-1
Tensile Strength	16 MPA	ASTM D412

Purposes



Abrasive Resistance



Wear Resistant

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.