

Data Sheet

Q855 Fire Retardant & Anti-Static Neoprene Rubber to UNE23727:1990 & NF16101

| | |
|--------------------|----------|
| Data Sheet Type | Final |
| Material Reference | Q855 |
| Polymer | CR |
| Date Issued | 18/04/25 |



Description

A Chloroprene/Neoprene Rubber designed for use in the Rail Industry, conforming with both UNE 23727:1990 & NF16101. This Rubber Sheetting is both Anti-Static & Flame Retardant - being of European Manufacture, this grade benefits from Full Test Results, Traceability & batch testing at each manufacturing process.

| Specifications | Values | Test Methods |
|---|------------------|----------------|
| Elongation at Break | > 450 % | ASTM D412 |
| Flame Resistance | to UNE23727:1990 | BS EN IEC61111 |
| Highest Recommended Working Temperature | 100 °C | None |
| Lowest Recommended Working Temperature | -25 °C | None |
| Shore Hardness (Shore A) | 60 ° Shore | ASTM D2240 |
| Specific Gravity | 1.45 g/cm 3 | ASTM D2240 |
| Tensile Strength | > 10 MPA | ASTM D412 |

Purposes



Anti-Static



Flame Retardant



Ozone Resistance



Weather Resistance

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.