

Data Sheet		Q856 Neoprene(CR) Self Extinguishing NF-F16101 M2 F3 Neoprene	
Data Sheet Type	Final		
Material Reference	Q856	And Secundary	REACH
Polymer	CR Flame Retardant		
Date Issued	01/11/25		

Description

An European Manufactured Neoprene (Chloroprene - CR) Self Extinguishing Rubber Sheeting. Manufactured to the NF-F16101 standard meeting classification M2 F3

Specifications	Values	Test Methods
Elongation at Break	550 %	ASTM D412
Highest Recommended Working Temperature	100 °C	None
Lowest Recommended Working Temperature	-25 °C	None
Shore Hardness (Shore A)	65 ° Shore	ASTM D2240
Specific Gravity	1.69 g/cm 3	ASTM D2240
Tensile Strength	8 MPA	ASTM D412

Purposes







Self Extinguishing

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.