

Data Sheet

SI60

Data Sheet Type	Final
Material Reference	SI60
Polymer	Silicone
Date Issued	02/04/25



Description

SI60 Grade FDA Approved 60 Shore Silicone Sheeting - Available in White, Black, Blue, Translucent and Red

Specifications	Values	Test Methods
Compression Set	35 %	None
Elongation at Break	> 300 %	ASTM D412
Highest Recommended Working Temperature	200 °C	None
Intermittent Working Temperature	230 °C	None
Lowest Recommended Working Temperature	-60 °C	None
Shore Hardness (Shore A)	60 +/-5 ° Shore	ASTM D2240
Specific Gravity	1.25 +/-0.05 g/cm 3	ASTM D792
Tear Resistance	> 18 KN/m	ASTM D624 Die B
Tensile Strength	> 7 MPA	ASTM D412

Purposes



Food Contact Suitability



High Working Temperature

**Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.